

## Specification

# SODIUM SELENITE

$\text{Na}_2\text{SeO}_3$  spray dried  
for technical applications

06006



**RETORTE**  
AURUBIS GROUP



## Product features



$\text{Na}_2\text{SeO}_3$ : 99.8 % min    Se: 45.5 % – 45.9 %



Impurities in dry matter

|                |              |
|----------------|--------------|
| <b>Arsenic</b> | 12 ppm max.  |
| <b>Cadmium</b> | 5 ppm max.   |
| <b>Copper</b>  | 5 ppm max.   |
| <b>Iron</b>    | 10 ppm max.  |
| <b>Mercury</b> | 0.1 ppm max. |

|                          |              |
|--------------------------|--------------|
| <b>Nickel</b>            | 5 ppm max.   |
| <b>Lead</b>              | 10 ppm max.  |
| <b>Tellurium</b>         | 100 ppm max. |
| <b>Moisture*</b>         | 0.2 % max.   |
| <b>Insoluble residue</b> | 0.15 % max.  |



Granulometry (typical values, not guaranteed)

100 % < 1.000 mm (18 mesh)    99.8 % < 0.300 mm (50 mesh)    25 % < 0.045 mm (325 mesh)



Bulk density: 0.9 – 1.1 kg/l



Odour: none



Appearance: white crystallin powder

## Packaging & Transportation



Packaging

25 kg net steel drums with liner



Transportation

ADR class 6.1, PG I, UN 2630,  
IMDG Code 6.1



Not intended for human, feed or veterinary use.

\* when packed

*This specification may be subject to changes.*

*Attention! In case of unauthorized copy or modification, the contents are not valid.*

© Retorte GmbH

Na2SeO3\_sd\_technical applications/05/220819